

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 July 2003 (03.07.2003)

PCT

(10) International Publication Number
WO 03/054040 A1

- (51) International Patent Classification⁷: **C08F 14/06**, 4/32, 4/38
- (21) International Application Number: **PCT/EP02/14518**
- (22) International Filing Date:
18 December 2002 (18.12.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/342,434 21 December 2001 (21.12.2001) US
- (71) Applicant (for all designated States except US): **AKZO NOBEL N.V.** [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **WESTMIJZE, Hans** [NL/NL]; Burg. Boreellaan 1, NL-7437 BB Bathmen (NL). **VAN SWIETEN, Andreas, Petrus** [NL/NL]; Reinaldstraat 6, NL-6883 HM Velp (NL). **MEULENBRUGGE, Lambertus** [NL/NL]; De Gemeint 11, 6931 HZ Westervoort (NL). **VANDUFFEL, Koen, Antoon, Kornelis** [NL/NL]; Stevinhof 18, 7424 AH Deventer (NL).
- (74) Agent: **SCHALKWIJK, Pieter, Cornelis**; Akzo Nobel N.V., Intellectual Property Department (Dept. AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 03/054040 A1

(54) Title: CONTINUOUS DOSING OF EXTREMELY FAST INITIATORS DURING POLYMERIZATION REACTIONS

(57) Abstract: The invention pertains to a process wherein initiators having a half-life from 0.0001 hour to 0.05 hour at the polymerization temperature are dosed to a polymerization mixture. The dosing of such initiator allows improved control of the polymerization rate and faster polymerization rates, and the process will render a polymer with very low residual initiator levels.

CONTINUOUS DOSING OF EXTREMELY FAST INITIATORS DURING POLYMERIZATION REACTIONS

5

The present invention relates to a process to polymerize or copolymerize vinyl chloride monomer wherein one or more organic initiators are dosed to the polymerization mixture at the reaction temperature during said polymerization.

10 Such a process is known from WO 00/17245, wherein initiators are dosed to a polymerization reactor at temperatures where the initiators have a half-life of from 0.05 to 1.0 hour. It is noted that the lower limit of this range (presenting the most reactive initiators) reflects the current opinion of the skilled person in the field that one cannot use a too reactive initiator for safety and efficiency reasons. More
15 specifically, hitherto it has always been expected that initiators with a half-life of 0.05 hour or less at conventional polymerization temperatures (especially for initiators to be used at temperatures from 35°C to 84°C) could not be handled and transported safely because of the inherent instability of the products. Furthermore, these so-called "extremely fast initiators" were not expected to
20 efficiently polymerize monomers, since they were expected to give all types of side-reactions, such as hydrolysis, carboxy-inversion (for instance, wherein a peroxyester is converted to the corresponding carbonate, or a diacylperoxide to the corresponding anhydride), and other types of (in-cage) rearrangement reactions, leading to an unacceptably low initiation efficiency. Indeed, an
25 evaluation of the performance of extremely fast initiators in the more conventional processes, wherein all peroxide is dosed at once, showed they had a low efficiency.

The current invention relates to a new process wherein extremely fast initiators
30 are dosed to a reactor during a polymerization reaction. Preferably, said polymerization is conducted at temperatures from 35°C to 84°C. Preferably, the new process is a conventional process in which vinyl chloride monomer is

polymerized and wherein extremely fast initiators are dosed during the polymerization. However, the new invention is also suitable for developing a continuous process for the polymerization of vinyl chloride. The process according to the invention gave unexpectedly high initiator efficiency and allowed
5 even better control of the heat of polymerization being developed, allowing optimum reactor space-time yield, and even lower residual initiator levels in the resin after polymerization, compared to the process and products of WO 00/17245. Accordingly, a resin with even improved heat stability properties and low fish-eye levels was obtained, while the polymerization time could be
10 shortened.

The new process is characterized in that extremely fast organic initiators are used in the polymerization process, which initiators have a half-life from 0.0001 hour to 0.050 hour at the polymerization temperature, more preferably from 0.001 to
15 0.050 hour, most preferably from 0.002 to 0.050 hour. It is noted that the term "to 0.050 hour" does not comprise the value 0.050. The dosing of such initiator allows improved control of the polymerization rate, higher polymerization rates, leading to an increased space-time yield of polymerization reactors, and results in the process rendering a polymer with very low residual initiator levels.

20

The process according to the invention is pre-eminently suited to polymerize monomer mixtures comprising vinyl chloride monomer (VCM). Preferably, the process according to the invention involves the polymerization of monomer mixtures comprising at least 50% by weight (% w/w) of VCM, based on the weight
25 of all monomer. Comonomers that can be used are of the conventional type and include vinylidene chloride, vinyl acetate, ethylene, propylene, acrylonitrile, styrene, and (meth)acrylates. More preferably, at least 80% w/w of the monomer(s) being polymerized is made up of VCM, while in the most preferred process the monomer consists essentially of VCM. As is known in the art, the
30 polymerization temperature of such processes to a large extent determines the molecular weight of the resulting resin.

In the process according to the invention, one or more initiators may be used additionally, as long as at least one extremely fast initiator is dosed during part of the polymerization process. Preferably, all initiator used in the process has a half-life of at most 10% of the polymerization time at the polymerization temperature (or average polymerization temperature), so that the resin obtained by this process is essentially free of residual initiator. Preferably, the initiator is an organic peroxide. In another preferred embodiment, all initiator used in the polymerization process is extremely fast.

Preferred examples of processes according to the invention are processes wherein one or more of the following initiators are used:

- Hexanoyl pivaloyl peroxide, with a half-life of less than 0.05 hr at temperatures greater than 38°C,
- 1,1,3,3-tetramethylbutylperoxy methoxy acetate, with a half-life of less than 0.05 hr at temperatures greater than 59°C,
- 2,2-bis(2,2-dimethylpropanoylperoxy)-4-methyl pentane, with a half-life of less than 0.05 hr at temperatures greater than 61°C,
- diisobutanoyl peroxide, with a half-life of less than 0.05 hr at temperatures greater than 64°C,
- bis(tert-butylperoxy) oxalate, with a half-life of less than 0.05 hr at temperatures greater than 67°C,
- 2-(2,2-dimethylpropanoylperoxy)-2-(2-ethylhexanoylperoxy)-4-methyl pentane, with a half-life of less than 0.05 hr at temperatures greater than 69°C,
- α -cumyl peroxyneodecanoate (Trigonox® 99), with a half-life of less than 0.05 hr at temperatures greater than 81°C,
- 2,4,4-trimethylpentyl-2-peroxyneodecanoate, with a half-life of less than 0.05 hr at temperatures greater than 83°C,

while they are dosed to a polymerization reaction mixture at or above the mentioned temperature at which the half-life is 0.05°C, more preferably at a

temperature from the mentioned temperature at which the half-life is 0.05°C up to 84°C.

Other initiators can also be used. For screening purposes, the initiators can be
5 classified on the basis of their half-lives as determined by conventional thermal
decomposition studies in monochlorobenzene, as is well known in the art (see for
instance the brochure "Initiators for high polymers" with code 10737, obtainable
from Akzo Nobel), and in accordance with the principles set out above. However,
the value which is decisive for the half-life of the initiator is as presented in said
10 brochure or, if it is not, the half-life as measured in a well-mixed model system
being equal to the polymerization recipe in which the initiator is to be used, but
wherein the monomer is replaced by 1-chlorobutane.

If so desired, a conventional peroxide with a half-life of from 0.05 to 5 hours,
15 preferably from 0.05 to 3 hours, more preferably from 0.05 to 2 hours, at the
polymerization temperature can be used in conjunction with the extremely fast
initiators according to the invention, but this is less preferred. If a conventional
initiator is used, it is advantageous to select it such that at the end of the
polymerization, the residual level is at an acceptably low level. Typically, this
20 means that if a conventional initiator is used, it will preferably be introduced into
the reaction mixture prior to or just after the heat-up step, when the conversion, or
the degree of polymerization, is below 80, preferably below 50, more preferably
below 30, even more preferably below 10, and most preferably below 2% of all
monomer used in the process.

25

It is furthermore preferred that two steps are present in the process. In a first step
with a duration of up to 60 minutes, preferably up to 45 minutes, and more
preferably up to 35 minutes, and with a minimum duration of 1 minute, preferably
of 5 minutes, more preferably of 10 minutes, from 10 to 60% w/w, preferably from
30 10 to 40% w/w, of all initiator is dosed, such that the desired cooling capacity,
preferably the maximum one, more preferably the maximum cooling capacity that
is acceptable from a safety point of view, is reached at the end of this dosing

step. Then, in a second step, the remaining initiator is dosed (added over time) to control the polymerization in such a way that the desired cooling capacity, preferably the maximum one available, more preferably the maximum cooling capacity that is acceptable from a safety point of view, is matched. Preferably, at
5 least part of said second step involves dosing of initiator when the monomer conversion is greater than 40% w/w, more preferably greater than 60% w/w.

In this process it can be preferred to use extremely fast initiators and/or one or more conventional initiators during the polymerization stage wherein the content
10 of the reactor is heated up to the desired polymerization temperature, the so-called cold-start process, since such a use can increase the space-time yield of the reactors.

It can be beneficial to introduce up to 4% w/w, more preferably up to 2% w/w,
15 most preferably up to 1% w/w, of all extremely fast initiator immediately after the formation of the reaction mixture, in order to start the polymerization process. This procedure is particularly preferred if a certain amount of polymerization inhibitor (a radical trapping species) is present in the reaction mixture. If such a radical scavenger is present, for instance because it is introduced with the
20 monomer wherein it is typically used as a stabilizer, the initially dosed initiator will react with said scavenger, thus preventing a delayed start of the polymerization reaction.

The initiator can be a redox initiation system. In such a case the reducing agent,
25 the oxidizing agent, or both can be dosed in accordance with the invention. For such redox systems, the half-life of the redox system is the half-life as measured when all components of the system are present. However, in view of the fact that redox systems typically contain heavy metals and/or undesired reducing agents, the initiators of the present invention preferably are not such redox initiation
30 systems.

The amount of initiator to be used in a process according to the invention is within the range conventionally used in polymerization processes. Typically, from 0.01 to 2% w/w of initiator, preferably 0.01-1% w/w, more preferably 0.01-0.5% w/w, based on the weight of the monomer(s) to be polymerized, is used.

5

The initiator is dosed to the reactor in the pure form or, preferably, in the form of a dilute solution or dispersion (such as a suspension or emulsion). One or more suitable solvents can be used to dilute the initiator. Preferably, such solvents are easily removed during the steps in which the polymer is worked up after the polymerization process, as with alcohols, or they are of such a nature that it is acceptable to leave them as a residue in the final polymer, as is the case for solvents that are desired plasticizers for the final resin. Furthermore, it can be advantageous, but is not necessarily required, that such solvents do not adversely affect the thermal stability of the initiator dissolved therein, as can be verified by analyzing the half-life temperature of the initiator in said solvent. An example of such a solvent is isododecane. If an initiator dispersion is dosed, then it can be a dispersion of either the initiator itself or of a solution of the initiator, preferably in said suitable solvents. Preferably, the dispersion is an aqueous dispersion. Preferably, the initiator is dosed in a concentration of 0.1 to 60% w/w, more preferably 0.5 to 25% w/w, and most preferably 2 to 15% w/w. The more dilute initiator solutions or dispersions ensure rapid mixing of the initiator and the polymerization mixture, which leads to a more efficient use of the initiator, which is crucial for the extremely fast initiators that are used.

It is to be understood that the word "dosing" is used to describe the step of adding peroxide to the polymerizing reaction mixture at polymerization conditions. The dosing can be done intermittently during the polymerization over a period of time wherein preferably at least 20%, preferably at least 40%, more preferably at least 60%, of all monomer used in the process is polymerized, meaning that at least two portions of initiator are added to the reaction mixture, or it can be continuous, meaning that for a certain period of time the initiator is continuously added to the reaction mixture, or any combination of these techniques. Examples

30

of a combination of such techniques include, for instance, a process wherein the initiator is first added continuously, then the addition is stopped, and then again it is added continuously. If an intermittent operation is selected, there are at least 2, preferably at least 4, more preferably at least 10, and most preferably at least 20 moments at the polymerization temperature at which the initiator is dosed.

Most preferably, the peroxide is dosed continuously and/or intermittently from the start of the polymerization reaction, preferably after at least 5%, more preferably at least 10%, even more preferably at least 20%, most preferably at least 30%, of the monomer(s) has already been polymerized and wherein during the dosing period at least 2, preferably at least 5, more preferably at least 10%, more preferably at least 20%, more preferably at least 30%, and most preferably at least 50%, of all monomer used in the process is polymerized.

Preferably, the dosing can be effected at any suitable entry point to the reactor. If water is added in the course of the polymerization process, for example to compensate for the shrinkage of the reactor content due to the polymerization reaction, it can be advantageous to use the line through which this water is dosed to also dose the initiator. It is noted that if the formation of the initiator is fast enough, one can dose the raw materials for said initiator into piping or hold-up vessels, from which the initiator is then fed into the polymerization mixture. Alternatively, but less desired, there is the process wherein the raw materials are added to the polymerization mixture. In all instances it can be beneficial to add stirring equipment and/or heat exchangers to the feed lines in order to optimize efficiency.

The polymerization process can be conducted as a mass process wherein the reaction mixture is predominantly monomer or as a suspension process wherein the reaction mixture typically is a suspension of monomer in water, or as an emulsion or micro-emulsion process wherein the monomer typically is emulsified in water. In these processes the usual additives will have to be used. For example, if the monomer is present in the form of a suspension in water, the usual additives like surfactant(s), protective colloid(s), anti-fouling agent(s), pH-

buffer(s), etc. may be present. Depending on the type of polymer desired, each of the above-mentioned processes may be preferred. The process according to the invention is especially suited for mass and suspension processes.

5 Because the polymerization rate can be controlled very adequately, the polymerization process becomes safer. More specifically, when the dosing of the initiator is stopped, the polymerization process halts almost instantaneously. This means that where a conventional process rate is limited for safety reasons (peroxide is present and a too high concentration will lead to an uncontrollable
10 run-away reaction), the present process is not hampered by such safety restrictions. Hence with the present process much faster polymerization rates can be achieved because much higher peroxide loads can be applied. It is therefore that we claim, in a preferred embodiment, all conventional polymerization processes wherein extremely fast peroxides are dosed and wherein at least 80%
15 of all monomer is polymerized within a period of 2 hours. Preferably, at least 85% of the monomer is polymerized within 2 hours. Most preferably, at least 85% of all monomer is polymerized within 110 minutes.

The fact that such very high polymerization rates can be achieved opens up the
20 possibility to polymerize or copolymerize vinyl chloride in accordance with the present invention in a continuous fashion, or in a combination of batch and continuous fashions. The skilled person will have no difficulty in converting the above information, as presented for batch operations, into a (semi-)continuous operation mode. As an example, it is noted that in order to achieve a good control
25 over the polymerization rate in a continuous tube-like reactor, it is necessary to add the initiator at various addition points in the reactor, with the addition rate having to be chosen such that the polymerization rate is adequate until the next addition point. Hence, in such a case typically a multitude of controlling and addition points will be necessary.

30

After the polymerization, the resulting (co)polymer (or resin) will be worked up as is usual in the art. Polymers obtained by a suspension polymerization according

to the invention, for example, will be submitted to the usual drying and screening steps. The resulting resin preferably is characterized in that it contains less than 50 ppm of residual initiator, more preferably less than 40 ppm, and most preferably less than 25 ppm of initiator, immediately after drying for 1 hour at 60°C and screening. The resin was found to exhibit excellent heat stability as measured with a Metrastat® PSD260 testing oven according to method ISO 182-2 (1990E). The improved heat stability proved that the resin hardly discoloured when submitted to melt-processing steps, e.g., to form shaped articles.

10

Experimental

In a standard suspension polymerization experiment, a temperature controlled 1-litre stainless steel Büchi reactor provided with one baffle, two flat-bladed stirrers at three levels, a pressure transducer, a vinyl chloride (VCM) feed line, and a nitrogen purge line was charged with: 425 g of demineralized water, 5 g of a 5% solution of Alcotex® B72 (polyvinylacetate/alcohol) in demineralized water, and pressurized to 15 barg, using nitrogen. If no leaks are observed, the reactor is evacuated and pressurized with nitrogen up to 5 barg three times to flush out virtually all air. If not all initiator is dosed, then the desired amount of initiator is added. Next, the reactor was evacuated and charged with 250 g VCM ex Akzo Nobel Salt & Base, followed by heating up of the reactor to the polymerization temperature of 68°C in 30-60 minutes. After a pressure drop in the reactor, or 4.5 hours of reaction time, whichever took shorter, the polymerization was continued for another half hour, and then the reactor was cooled to 20-25°C, evacuated, and freed of virtually all remaining VCM. The polymer was obtained after filtration, washing, and drying (at 60°C for 1 hour using a fluidized bed).

The initiator(s) used, the amount dosed, the dosing procedure, and the polymerization results are presented in Table 1.

The heat formed during the polymerization process is measured and cooling adapted to the heat formed. The more heat is generated at a certain time, the

more difficult it will be to control the temperature of the reaction mixture. A low heat peak together with high polymer yields is preferred, since then an optimum in the space-time yield of the reactor can be attained. However, since in a continuous process cooling is easier, especially such types of reactors would
5 allow even higher peroxide concentrations.

Example 1

After reaching the polymerization temperature, 500 ppm of pure diisobutanoyl peroxide (calculated on VCM), used as Trigonox® 187 at a concentration of 1%
10 in isododecane, was dosed to the reaction mixture over a period of 30 minutes. Thereafter the dosing speed was reduced to roughly 300 ppm of diisobutanoyl peroxide per hour (using the same solution) over a period of 2.5 hrs in such a way that the cooling capacity necessary to keep the reaction mixture at the polymerization temperature was kept constant. A pressure drop was observed.
15 The results are mentioned in Table 1

Comparative Example A

After reaching the polymerization temperature, 1,250 ppm of pure diisobutanoyl peroxide (calculated on VCM), supplied as Trigonox® 187 in a 30% solution in
20 isododecane, was added within two minutes.
After 5 hours of reaction time the polymerization was stopped and worked up as described in the experimental procedure. The yield is mentioned in Table 1.

Table 1: Expected results of VCM suspension polymerization with Trigonox® 187 at 68°C according to procedures for continuous dosing and for warm start.

	Example 1	Comparison
	Continuous dosing	Warm start
	500 ppm added during 30 minutes and subsequently 300 ppm /hr during 2.5 hrs	Peroxide added in 2 minutes at polymerization time
Peroxide quantity used	1,250 ppm	1,250 ppm
Constant pressure time	2.5 hrs	No pressure drop
Polymerization time	3 hrs	5 hrs
PVC yield	85%	25%

Examples 2 and 3

- 5 Example 2 was carried out according to the same procedure as Example 1, but the temperature was increased to 82°C and the peroxide concentration and dosing were slightly altered, as can be seen in Table 2. The Trigonox® 187 was dosed as an aqueous emulsion with a concentration of 1% ww.

10 In Example 3 VCM was polymerized in a 10-litre reactor at 68°C, instead of using the 1-l scale. The starting ratio of VCM / water was 1 / 1.4. The initiator was dosed as an emulsion with a concentration of 1%

Table 2: The results of VCM suspension polymerization with Tx 187 according to the procedure for continuous dosing

	Example 2	Example 3
Polymerization temperature	82°C	68°C
T (½) initiator	0.006 hr	0.03 hr
Scale	1 Litre	10 Litres
PVA	1,000 ppm Alcotex B72 500 pp Alcotex B78	415 pp Alcotex B72 100 ppm GH 23 (ex Gohsenol) 50 ppm Alcotex 552P
Peroxide quantity used	1,185 ppm Trigonox 187 on VCM	1,660 ppm Trigonox 187 on VCM
Dosing procedure	200 ppm peroxide added during 12 minutes and subsequently 985 ppm during 220 minutes	960 ppm peroxide added during 12 minutes and subsequently 700 ppm peroxide during 50 minutes
Polymerization rate	30% / hr	90% / hr
Constant pressure time	147 min	50 min
Pressure drop rate	9 bar/hr	22 bar/hr
Polymerization time	3 hrs	1.2 hrs
PVC yield	84%	91%

The resulting PVC contained less than 25 ppm of residual peroxide after drying.

Claims

1. Process to polymerize vinyl chloride monomer and optional further monomers using one or more initiators, with at least part of said initiators being dosed to the polymerizing reaction mixture, characterized in that at least one organic initiator with a half-life of from 0.0001 hour to 0.050 hour at the polymerization temperature is dosed to the polymerizing reaction mixture at said polymerization temperature.
2. A process according to claim 1 comprising a step wherein at least part of the dosing of one or more of the initiators is controlled such that the desired cooling capacity of the reactor is used, preferably while keeping the temperature of the polymerization mixture constant.
3. A process according to claim 1 or 2 wherein at least part of the initiator(s) is dosed after at least 40% w/w, preferably at least 60% w/w, of all monomer has been polymerized.
4. A process according to any one of claims 1-3 wherein the initiator(s), or part of the initiator(s), is (are) dosed, intermittently and/or continuously, during a period wherein at least 20% of all monomer used in the polymerization is polymerized.
5. A process according to any one of claims 1-3 wherein the initiator(s), or part of the initiator(s), is (are) dosed, intermittently and/or continuously, and wherein during the dosing period at least 2% of all monomer used in the process is polymerized.
6. A process according to any one of the preceding claims wherein essentially all of the initiator(s) is (are) selected from the group consisting of organic peroxides.

7. The process of claim 6 wherein essentially all initiator(s) has (have) a half-life of from 0.0001 hour to 0.050 hour at the polymerization temperature.
- 5 8. Vinyl chloride based (co)polymer obtainable by any one of the processes of claims 1-6, having less than 50 parts by weight of residual initiator, based on one million parts by weight of the (co)polymer, when measured immediately after polymerization and drying of the (co)polymer for 1 hour at 60°C.
- 10 9. Use of a vinyl chloride (co)polymer according to claim 7 in a shaping process involving the heating of the co(polymer) to above its melting temperature.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/14518

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F14/06 C08F4/32 C08F4/38

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 17245 A (AKZO NOBEL NV ;SCHUT JACOBUS (NL); WESTMIJZE HANS (NL); SWIETEN AN) 30 March 2000 (2000-03-30) cited in the application claims page 3, line 12-24 page 2, line 1-9	1-9
A	EP 0 096 365 A (AIR PROD & CHEM) 21 December 1983 (1983-12-21) the whole document	
A	EP 0 492 712 A (AKZO NV) 1 July 1992 (1992-07-01) the whole document	

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

25 March 2003

Date of mailing of the international search report

02/04/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Baekelmans, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/14518

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0017245	A	30-03-2000	AU 5862499 A	10-04-2000
			BR 9913993 A	03-07-2001
			CA 2344824 A1	30-03-2000
			CN 1323323 T	21-11-2001
			WO 0017245 A1	30-03-2000
			EP 1124866 A1	22-08-2001
			HU 0104277 A2	28-03-2002
			JP 2002526574 T	20-08-2002
			NO 20011413 A	03-05-2001
			PL 346757 A1	25-02-2002
			SK 3982001 A3	03-12-2001
			TR 200101491 T2	21-12-2001
			US 2002123591 A1	05-09-2002
			US 6384155 B1	07-05-2002
EP 0096365	A	21-12-1983	EP 0096365 A1	21-12-1983
			JP 59001516 A	06-01-1984
EP 0492712	A	01-07-1992	CA 2058347 A1	25-06-1992
			EP 0492712 A1	01-07-1992
			JP 4318002 A	09-11-1992